



Pacmaan[®] NA 747FG

Aramid fibre braided packing impregnated with PTFE

- · One of the best sealing solutions for abrasive media such as stock, juice (sugar), slurries, fly ash, ash slurry etc
- High degree of resiliency and consistency of volume
- · Special PTFE impregnation process to avoid shaft erosion and start up friction
- · Interlock braiding for high pressure and extrusion resistance
- Shaft/sleeve hardness should be > 45 HRC: If not, please consult us
- Food Grade certified as per Commission Regulation (EU) No 10/2011 of 14 January 2011 and Article 3 of European Regulation No. 1935/2004

Service Media and Conditions Magma, massecuite, juice pumps, stock, ash slurry, mud slurry, fly ash water, sewage, highly abrasive bleach or wood pulp, wash water, raw water and turbid water, chemical slurries etc -100°C to 280°C Temperature Pressure 200 bar (static), 35 bar (rotary), 200 bar (reciprocating) 20 m/sec (rotary), 10 m/sec (reciprocating) Shaft Speed рΗ 1 to 13 Applications Pump, agitators

Available in rope and ring form

9B Dr Martin Luther King Sarani, 2nd Floor Kolkata 700 016, India Phone +91 33 4050 1000 | Fax +91 33 4050 1075 | Email comments@jdjones.com